

TEST RECORD SHEET SS1

Solvent & Sealant Testing	
Date:	20.02.13
Sealant tested:	N/A
Solvent used/ tested:	FABRICATOR Solvent Cleaner 7805
Manufacturer:	Glasscorp

Powder type:	Polyester	TGIC Free:	✓
Manufacturer:	Dulux Powder & Industrial Coatings		

	Colour (ΔE)		Pencil Hardness		Gloss (60°)	
	Silver Star Kinetic	LSG Matt New Denim Blue	Silver Star Kinetic	LSG Matt New Denim Blue	Silver Star Kinetic	LSG Matt New Denim Blue
Before testing	0.00	0.00	H	2H	58.2	25.1
After solvent	0.42	0.45	H	2H	57.5	23.7
Exp after 501 hours QUV-B	1.95	6.67	H	2H	11.8	8.2
Unexp after 501 hours QUV-B	2.23	7.17	H	2H	12.3	8.7
PASS Y / N	Y	Y	Y	Y	Y	Y
Comments:	Results averaged over sample set of 3 for each colour.					

Conclusion:

Test results obtained for the supplied solvents are in accordance with WANZ Sealants, Masking components and Powdercoat compatibility standard – V9 – 110204.

Glasscorp - FABRICATOR Solvent Cleaner 7805 is compatible for use on Duralloy powder coating products.

Analysed by:

Alexander Lauaki, Technical Services Chemist
 Technical & Innovation Laboratory
 Dulux Powder & Industrial Coating NZ Ltd
 Auckland 0627
 New Zealand

Disclaimer for WANZ Test Methods

This test method is one of many different tests that will be required to determine that a product is fit for purpose. This test method is specific to the materials being tested. The results cannot be applied to other similar products unless the test report so indicates.

WANZ does NOT endorse or approve any products and no such claims may be made as a result of any test report. Test results may be used commercially by simply stating the facts of the report.

WANZ, nor its officers, does not accept any liability for loss or damages incurred by any person or organization as a result of reliance on this test method. WANZ recommends that users make their own enquiries regarding the most appropriate test methods for their products.